



COLOURING YOUR IMAGINATION

JAKAZOL HLF DYES		PROCESSES							LIGHT FASTNESS								SOLUBILITY		WASHING			PERSPIRATION M&S C7													
		WARM EXHAUST	COLD PAD BATCH	PAD DRY PAD STEAM	PAD DRY STEAM	PAD DRY THERMORFIX	ECONTROL	DISCHARGEABILITY	AATCC 16E 1/1 SD	AATCC 16E 1/3 SD	AATCC 16E 1/6 SD	AATCC 16E 1/12 SD	ISO B02 1/1 SD	ISO B02 1/3 SD	ISO B02 1/6 SD	ISO B02 1/12 SD	gms/lit		CO6/C2			ACIDIC			ALKALINE										
																	WATER 30° C	IN PRESENCE OF SALT 50° C (90 G/L)	EFFECT	STAIN (COTTON)	STAIN (NYLON)	EFFECT	STAIN (COTTON)	STAIN (NYLON)	EFFECT	STAIN (COTTON)	STAIN (NYLON)	CHLORINATED WATER (JIS L 0884-10mg)	DRY RUBBING (M&S C8)	WET RUBBING (M&S C8)	PERBORATE WET FADE (M&S C9A)	REPEATED DOMESTIC WASHING (M&S C10A)			
																																	200	200	4-5
0.3%	1.0%	YELLOW HLF	S	S	S	S	S	B	4-5	4-5	4	4	6	5-6	5	4	200	200	4-5	4	4-5	4	4	4	4-5	4	4	4	4	4	4	4-5	4	4-5	4
			S	S	S	S	S	A	4-5	4	4	3-4	6	5	4-5	4	125	< 20	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	3-4	5	4	4-5	4			
		BLUE HLF	S	S	S	S	S	C	4-5	4-5	4	3-4	5-6	5-6	5	4-5	150	125	4-5	3-4	4-5	4	4	4	4	4	4-5	4	4-5	4	4-5	4			
			S	S	S	S	S	C	4-5	4-5	4	3-4	5-6	5-6	5	4-5	150	125	4-5	3-4	4-5	4	4	4	4	4	4-5	4	4-5	4	4-5	4			

Abbreviations

- BI - Bluer
- DI - Duller
- A - White Discharge
- B - Moderately Dischargeable
- C - Non Discharge
- S - Suitable
- NS - Not Suitable

Note: These shades are indicative, original shades may vary.