














COLOURING YOUR IMAGINATION

ILLUSTRATION	JAKAZOL ME DYES	% FASTNESS DEPTH	PROCESSES							DISCHARGEABILITY	LIGHT FASTNESS								SOLUBILITY		WASHING			PERSPIRATION M&S C7											
			WARM EXHAUST	COLD PAD BATCH	PAD DRY PAD STEAM	PAD DRY STEAM	PAD DRY THERMOFIX	ECONTROL	20AFU				GRADE-6				gms/lit		CO6/C2			ACIDIC			ALKALINE										
									AATCC 16E (1/1 SD)		AATCC 16E (1/2 SD)	AATCC 16E (1/3 SD)	AATCC 16E (1/6 SD)	ISO B02 (1/1 SD)	ISO B02 (1/2 SD)	ISO B02 (1/3 SD)	ISO B02 (1/6 SD)	WATER 30° C	IN PRESENCE OF SALT 50°C (90 G/L)	SHADE CHANGE	STAIN (COTTON)	STAIN (NYLON)	SHADE CHANGE	STAIN (COTTON)	STAIN (NYLON)	SHADE CHANGE	STAIN (COTTON)	STAIN (NYLON)	CHLORINATED WATER (JIS L 0884-10mg)	DRY RUBBING (M&S C8)	WET RUBBING (M&S C8)	PERBORATE WET FADE (M&S C9A)	REPEATED DOMESTIC WASHING (M&S C10A)		
 1/1 SD 2.8% 1/3 SD 0.8%	Jakofix Yellow ME4GL	2.8	S	NS	NS	NS	NS	NS	A	4	3-4	3-4	3	5-6	5	4-5	4	200	150	4 R	4-5	4-5	4 R	4-5	4-5	4-5	4-5	4-5	4-5	4 R	4-5	3-4	4-5	4 R	
 1/1 SD 3.3% 1/3 SD 1.1%	Jakofix Golden Yellow MERL	3.3	S	S	NS	NS	S	NS	C	4-5	4-5	4-5	4	6	5-6	5-6	5	200	200	4-5	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4 R	4-5	3-4	4-5	4 R	
 1/1 SD 2.6% 1/3 SD 0.8%	Jakofix Orange ME2RL	2.6	S	NS	NS	NS	NS	NS	C	3-4	3	3	2-3	4	3-4	3-4	3	20	<5	4-5	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	4-5	4 DI		
 1/1 SD 3.9% 1/3 SD 1.15%	Jakofix Red MEGF	3.9	S	S	NS	NS	NS	NS	A	3-4	3-4	3-4	3-4	4-5	4	4	3-4	200	<5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
 1/1 SD 3.1% 1/3 SD 0.98%	Jakofix Red ME3BL	3.1	S	S	NS	NS	NS	NS	C	4	3-4	3-4	3-4	4-5	4	4	3-4	80	<5	4-5 Y	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
 1/1 SD 3.2% 1/3 SD 1.1%	Jakofix Red ME4BL	3.2	S	S	NS	NS	S	NS	C	4	3-4	3-4	3	4-5	4	4	3-4	200	100	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
 1/1 SD 2.7% 1/3 SD 0.88%	Jakofix Red ME6BL	2.7	S	NS	NS	NS	NS	NS	C	3-4	3-4	3-4	3	4-5	4	4	3	60	<5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
 1/2 SD 2.0% 1/3 SD 1.2%	Jakofix Brill Blue JRF	2.0	S	NS	NS	NS	NS	NS	B		4	4	4		6	5-6	4-5	60	<5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	
 1/2 SD 2.6% 1/3 SD 1.75%	Jakofix Brill Blue ME2RL	2.6	S	NS	NS	NS	NS	NS	C		2-3	2	2		2-3	2-3	2	200	150	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
 1/1 SD 3.45% 1/3 SD 1.15%	Jakofix Navy Blue ME2GL	3.45	S	NS	NS	NS	NS	NS	C	3	3	3	3	3-4	3	3	2-3	80	<5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4	4	4	
 1/1 SD 3.15% 1/3 SD 1.05%	Jakofix Navy Blue MEBF	3.15	S	NS	NS	NS	S	NS	B	3-4	3	3	3	4	3-4	3-4	3	200	120	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	3-4	4-5	3	4

Abbreviations
 BI-Bluer Br-Brighter Dk-Darker DI-Duller G-Greener R-Redder Y-Yellower S-Suitable NS-Not Suitable C-Non Dischargeable A-White Discharge B-Moderately Discharge

Note : This shades are indicative, original shades may vary
 Jay House, Panchvati Circle, Ambawadi, Ahmedabad-380 0006, Gujarat, India
 Phone: +91 79 2642 363 | Fax : +91 79 2642 5763 | Web:www.jaychemical.com