



COLOURING YOUR IMAGINATION

JAKOFIX P DYES			PROCESSES					LIGHT FASTNESS				SOLUBILITY		WASHING			PERSPIRATION M&S C7						CHLORINATED WATER (JIS L 0884-10mg)	DRY RUBBING (M&S C8)	WET RUBBING (M&S C8)	PERBORATE WET PADE (M&S C9A)	REPEATED DOMESTIC WASHING (M&S C10A)				
			PRINTING	COLD PAD BATCH	PAD DRY PAD STEAM	PAD DRY STEAM	PAD DRY THERMOFIX	ECONTROL	AATCC 16E 1/1	AATCC 16E 1/3	ISO BO2 1/1	ISO BO2 1/3	gms/lit		CO6/C2			ACIDIC			ALKALINE										
													WATER 30° C	IN PRESENCE OF SALT 50° C (90 G/L)	EFFECT	STAIN (COTTON)	STAIN (NYLON)	EFFECT	STAIN (COTTON)	STAIN (NYLON)	EFFECT	STAIN (COTTON)						STAIN (NYLON)			
																													WATER 30° C	IN PRESENCE OF SALT 50° C (90 G/L)	EFFECT
		BRILLIANT YELLOW P8G	S	NS	S	S	S	NS	4	4	5-6	5-6	120	< 5	4-5	4-5	4-5	4-5	5	5	4-5	4-5	4-5	4	4	4	5	4	R		
		YELLOW P6GS	S	NS	S	S	S	S	5	4-5	6	5	100	<20	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4	5	4			
		BRILLIANT YELLOW P4G	S	NS	S	S	S	S	5	4-5	6-7	6-7	100	< 5	4-5	4-5	4-5	4-5	4-5	5	4-5	4-5	4-5	4-5	4-5	4	5	4			
		YELLOW P2RN	S	NS	S	S	S	S	5	4-5	6-7	6	200	20	4-5	4	4-5	4	4	4	4-5	4-5	4	4-5	4-5	4-5	3-4	4-5	4	Br	
		ORANGE P3R	S	NS	S	S	S	NS	4	3-4	5	5	200	< 5	4-5	4-5	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4	Y	
		RED PB	S	NS	S	S	S	S	4	3-4	5-6	5	120	<20	4-5	4-5	4-5	4	4	4	4-5	4-5	4	4	4	4	4	4	4	Y	
		RED P4B	S	NS	S	S	S	S	4	3-4	4	3	200	100	5	4-5	5	4-5	4-5	4	4	4-5	4-5	4-5	4	4	4	4-5	4-5	4	Y
		RED P6B	S	NS	S	S	S	NS	4	3	4-5	3-4	100	<5	4-5	4-5	4-5	4-5	3-4	3	4-5	3-4	4	4	4	4	4	4	4		
		RED P8B	S	NS	S	S	S	NS	4	3-4	5	4-5	150	10	4-5	Y	4-5	4-5	4	4	4-5	4	4-5	4-5	4-5	4-5	4	4-5	4	Br	
		MAGENTA PB	S	NS	S	S	S	S	4	3-4	4	3-4	200	60	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3	DI	4-5	4	4	2		
		PURPLE P3R	S	NS	S	S	S	S	5	4-5	6	6	100	< 5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4	4-5	4-5	4	4-5	3-4	
		TURQUOISE PGR	S	NS	S	S	S	S	5	4-5	6-7	6	200	<5	4-5	4	4-5	4-5	4	4	4	4-5	3-4	4	4	4	3	3-4	4-5	4-5	Bl
		BRILLIANT BLUE P3R	S	NS	S	S	S	NS	5	4-5	6-7	6	200	200	4-5	R	4-5	5	4-5	4-5	4-5	4-5	4-5	4	4	4	4-5	4	4-5	4-5	Br
		BROWN P2R	S	NS	S	S	S	S	5	4-5	6	6	200	200	4	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4	4-5	4	4	5	4		
		BROWN P6R	S	NS	S	S	S	S	5	4-5	6-7	6	150	80	4-5	4-5	5	4	4	4	4	4	4	4	4	4-5	4	4-5	4	4-5	
		RED BROWN P4R	S	NS	S	S	S	NS	4-5	4	6	5	100	< 5	4	Y	3-4	4-5	4-5	4	4	4	4	4	4	3-4	4-5	4-5	4	4	
		BLUE P5R	S	NS	S	S	S	NS	4-5	4	6	5-6	60	< 5	4-5	R	4-5	4-5	4-5	4-5	4-5	4-5	3-4	G	4-5	4-5	3	R	4-5	3-4	Br
		NAVY P2R	S	NS	S	S	S	S	4	3-4	4	3-4	150	50	4-5	4-5	5	4	4	4-5	4-5	4	4	4	4	4	4-5	4	4-5	3-4	
		GREY PNG	S	NS	S	S	S	S	4	3-4	3-4	3	200	200	4-5	4-5	5	4-5	4-5	4-5	4-5	4	4	4	4	4	4-5	4	4-5	3-4	
		BLACK PN	S	NS	S	S	S	NS	4-5	(2/1)	-	5-6	(2/1)	60	10	4	G	4	4-5	4-5	4	3-4	4-5	3-4	4-5	4-5	4	4-5	3-4		
		BLACK PGR	S	NS	S	S	S	NS	4	(2/1)	-	5	(2/1)	200	80	5	4-5	5	5	4-5	4-5	5	4-5	4-5	3-4	G	5	4	4-5	4	

Abbreviations
 • Bl - Bluer • Br - Brighter • Dk - Darker • DI - Duller • G - Greener • R - Redder • Y - Yellower • A - White Discharge • B - Moderately Dischargeable • C - Non Discharge • S - Suitable • NS - Not Suitable

Note: These shades are indicative, original shades may vary.

Jay House, Pachvati Circle, Ambawadi, Ahmedabad - 380 006, Gujarat, INDIA.
 Phone: +91 79 2642 3363 | Fax: +91 79 2642 5763 | Web: www.jaychemical.com